


DESIGN LOAD REPORT

Part Description: P2073A (Post Base) Bending Moment

Report Date: August 11, 2022



Bending Direction	Avg. Ultimate Load (lbs)	Avg. Ultimate Bending Moment (in-lbs)	Allowed Bending Moment (in-lbs)
Strong	7,640	45,840	15,200
Weak	3,100	18,600	6,200

NOTES

1. Ultimate Loads per test C-128A
2. Allowed bending moment is based on average ultimate bending moment divided by SF3

Unistrut Engineering